

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 859 404 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

19.08.1998 Bulletin 1998/34

(51) Int. Cl.⁶: H01L 21/306

(21) Application number: 98100625.7

(22) Date of filing: 15.01.1998

(84) Designated Contracting States:

AT BE CH DE DK ES FI FR GB GR IE IT LI LU MC
NL PT SE

Designated Extension States:

AL LT LV MK RO SI

(30) Priority: 16.01.1997 JP 5610/97

16.01.1997 JP 5611/97

16.01.1997 JP 5612/97

(71) Applicants:

- Mitsubishi Materials Silicon Corporation
Chiyoda-ku, Tokyo (JP)
- MITSUBISHI MATERIALS CORPORATION
Chiyoda-ku, Tokyo (JP)

(72) Inventors:

- Matsuo, Chizuko
5-1 Ohtemachi 1-chome, Chiyoda-ku, Tokyo (JP)
- Kishimoto, Mikio,
c/o Central Research Institute
Omiya-shi, Saitama-ken (JP)
- Takaishi, Kazushige
5-1 Ohtemachi 1-chome, Chiyoda-ku, Tokyo (JP)


(74) Representative:

Dost, Wolfgang, Dr.rer.nat., Dipl.-Chem. et al
Patent- und Rechtsanwälte
Bardehle . Pagenberg . Dost . Altenburg .
Frohwitter . Geissler & Partner
Galileiplatz 1
81679 München (DE)

(54) Washing solution of semiconductor substrate and washing method using the same

(57) Disclosed is a washing solution of a semiconductor substrate which comprises 0.0001 to 0.1 % by weight of an organic acid and 0.005 to 0.25 % by weight of hydrofluoric acid and has pH of 2 to 4. When a contaminated substrate is immersed in a washing solution, a naturally oxidized film on the surface of the substrate is removed by hydrofluoric acid, and fine particles on the film, metal impurities and metal impurities in the film transfer to the liquid. Since the washing solution is an acidic solution containing an organic acid and having pH of 2 to 4, fine particles are charged to minus as those of the fine particles, and the metal impurities ions in the liquid becomes minus complex ions due to complexing effect of the organic acid. As the results, surface potentials of the respective fine particles and metal impurities are each minus which is the same as that of surface potential of the substrate so that adhesion or re-adhesion to the substrate can be prevented.

[Fig. 1]



EP 0 859 404 A2

Description

BACKGROUND OF THE INVENTION5 1. FIELD OF THE INVENTION

This invention relates to a washing solution for washing the surface of a semiconductor substrate such as a silicon wafer and a washing method using the same.

10 2. DESCRIPTION OF THE RELATED ART

On the surface of this kind of a semiconductor substrate, metal impurities or fine particles having a particle size of 1 μm or less are attached during the preparation process. Accompanying with high accumulation and high functionalization of a semiconductor device, it is more and more desired not to contaminated the surface of the semiconductor substrate by these metal impurities or fine particles, etc. Thus, washing technique of a semiconductor substrate is particularly important in the techniques of whole semiconductor devices.

As the conventional washing method of a semiconductor substrate, there has been known an RCA washing method using an SC1 solution comprising hydrogen peroxide and ammonium hydroxide, and an SC2 solution comprising hydrogen peroxide and a diluted hydrochloric acid. In the RCA washing method, a semiconductor substrate is firstly immersed in the SC1 solution to remove fine particles and organic residue from the substrate by the oxidizing and alkaline properties of the solution. That is, in the SC1 solution, both reactions of oxidization and reduction are simultaneously carried out, and reduction due to ammonia and oxidization due to hydrogen peroxide occur in the same bath competitively, and simultaneously, fine particles are removed from the substrate surface by lifting off due to an etching effect of the ammonium hydroxide solution. Then, the semiconductor substrate is immersed in an acidic solution of the SC2 solution to remove alkali ions or metal impurities which are insoluble in the SC1 solution.

On the other hand, Japanese Laid-Open Patent Application No. 94458/1995 discloses a washing solution of a semiconductor substrate which prevents metal impurities in a washing solution from adhering to the substrate surface when the semiconductor substrate is washed or prevents metal impurities once removed from the substrate surface from adhering to the substrate surface again, and inhibits unnecessary growth of a naturally oxidized film, and a washing method using the same. This washing solution is constituted by an acidic solution such as hydrofluoric acid containing 0.0001 to 0.001 % by weight of ammonia or 0.0005 to 0.01 % by weight of ethylenediaminetetraacetic acid (EDTA). In this washing solution, pH thereof is maintained to 1 or so in order to remove an oxidized film. According to this washing method, when a semiconductor substrate 1 is immersed in a washing solution 5 as shown in Fig. 6, removal of a naturally oxidized film 2 and removal of metal impurities 4 are simultaneously proceed, and a metal element shifted over to the washing solution forms a complex, or a metal complex salt 7 whereby it is masked. The surface of the semiconductor substrate 1 is charged to minus in the acidic solution while the surface of the metal complex salt 7 is also charged to minus by forming a complex ion in the acidic solution so that the metal complex salt, i.e., a metal element is prevented from adhering again to the substrate.

However, in the above-mentioned RCA washing method, metal impurities and fine particles which contaminate the substrate are removed by two baths so that washing steps are complicated such as washing of a chemical solution and washing accompanied thereby. Also, two kinds or more of acid and alkaline solutions are required as chemical solutions for washing. According to the above, there are disadvantages that this washing method requires a longer washing time, a washing device is a large-sized and a washing cost becomes expensive.

Also, according to the washing method described in Japanese Laid-Open Patent Application No. 94458/1995, as shown in Figs. 6(c) and 6(d), the surfaces of fine particles 3 are charged to plus in a washing solution 5 of strong acid so that even when metal impurities 4 can be removed from the semiconductor substrate 1 by the reason as mentioned above, there is a disadvantage that fine particles 3 are adhered to the surface of the substrate 1 and cannot be removed.

Further, the above-mentioned RCA washing method occurs two reactions of oxidation and reduction in the same bath competitively. Thus, firstly, metal impurities liberated from the substrate surface is retained in the SC1 solution whereby they are sometimes adhered again to the substrate surface depending on the surface potential, and secondly, even when a metal complex salt is to be formed by complexing metal ions in the SC1 solution, an organic acid is subjected to oxidation-reduction treatment in the SC1 solution whereby its complexing effect is markedly lowered. Accordingly, there is a problem that metal impurities cannot sufficiently be removed by the RCA washing method depending on the kind of a metal.

SUMMARY OF THE INVENTION

An object of the present invention is to provide a washing solution of a semiconductor substrate for removing well both of metal impurities and fine particles adhered to the surface of the semiconductor substrate and a washing method using the same.

An invention of Claim 1 relates to a washing solution of a semiconductor device containing 0.0001 to 0.1 % by weight of an organic acid and 0.005 to 0.25 % by weight of hydrofluoric acid and having pH of 2 to 4.

An invention of Claim 2 is an invention relating to Claim 1 and comprises a washing solution wherein the organic acid is one or more organic acid selected from the group consisting of citric acid, succinic acid, ethylenediamine-tetraacetic acid (hereinafter abbreviated to as EDTA), tartaric acid, salicylic acid, oxalic acid, acetic acid and formic acid.

An invention of Claim 3 relates to a method of washing a semiconductor substrate which comprises washing a semiconductor substrate with a washing solution containing 0.0001 to 0.1 % by weight of an organic acid and 0.005 to 0.25 % by weight of hydrofluoric acid and having pH of 2 to 4.

An invention of Claim 4 is an invention relating to Claim 3 and comprises a washing method wherein the organic acid is one or more organic acid selected from the group consisting of citric acid, succinic acid, EDTA, tartaric acid, salicylic acid, oxalic acid, acetic acid and formic acid.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a drawing showing a washing mechanism when washing is carried out by using a washing solution according to Claim 1 of the present invention.

Fig. 2 is a drawing showing another washing mechanism when washing is carried out by using a washing solution according to Claim 1 of the present invention.

Fig. 3 is a drawing showing a washing mechanism when washing is carried out by using a washing solution according to Claim 6 of the present invention.

Fig. 4 is a drawing showing a removing effect of Fe in Example and Comparative example when wavelength of an irradiated light is changed.

Fig. 5 is a drawing showing a metal impurity concentration at a wafer surface after washing in Example 47 and Comparative example 7.

Fig. 6 is a drawing showing a washing mechanism when washing is carried out by using the conventional washing solution.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

As shown in Figs. 1(a) and 1(b), a contaminated semiconductor substrate 11 is immersed in a washing solution 15. A naturally oxidized film 12 formed on the surface of the semiconductor substrate 11 is removed by hydrofluoric acid (HF) whereby fine particles 13 and metal impurities 14 on the naturally oxidized film 12 as well as metal impurities 14 contained in the naturally oxidized film are shifted over to the washing solution 15. Since the washing solution 15 is an acidic solution having pH of 2 to 4 and containing 0.005 to 0.25 % by weight of hydrofluoric acid and 0.0001 to 0.1 % by weight of an organic acid, the surfaces of the fine particles 13 are charged to minus which is the same as that of the surface of the substrate 11. Also, the metal impurities 14 liberated into the solution form a complex with organic acid molecules 16 to yield metal complex salts 17. This complex ion of the metal complex salt 17 is a minus ion. As a result, both of the surface potentials of the fine particles 13 and the metal impurities 14 become minus which is the same as that of the substrate 11 whereby adhesion or readhesion to the substrate can be prevented (Fig. 1(c)). When the semiconductor substrate 11 is pulled up from the washing solution 15, a substrate 11 the surface of which is cleaned can be obtained (Fig. 1(d)).

Also, as shown in Figs. 2(a) to 2(e), even when the washing solution 15 is contaminated by metals, when a contaminated semiconductor substrate 11 is immersed in the washing solution 15, a naturally oxidized film 12 formed on the surface of the semiconductor substrate 11 is removed by hydrofluoric acid whereby fine particles 13 and metal impurities 14 on the naturally oxidized film 12 as well as metal impurities 14 contained in the naturally oxidized film are shifted over to the washing solution 15. Here, metals contaminated the washing solution 15 also form a complex with organic acid molecules 16 as well as the metal impurities 14 liberated from the substrate in the solution to yield metal complex salts 17. Since this complex ion of the metal complex salt 17 is a minus ion, similarly as in Fig. 1, adhesion or re-adhesion of the fine particles 13 and metal impurities 14 to the substrate can be prevented, and when the semiconductor substrate 11 is pulled up from the washing solution 15, a substrate 11 the surface of which is cleaned can be obtained.

An invention according to Claim 5 relates to a method of washing a semiconductor substrate which comprises washing a semiconductor substrate with a washing solution containing 0.0001 to 0.1 % by weight of an organic acid and having pH of 2 to 4 while irradiating light with a wavelength of at least 500 nm.

A contaminated semiconductor substrate is immersed in a washing solution and light with a wavelength of at least 500 nm is irradiated to the surface of the substrate. By immersing the substrate in a washing solution, fine particles and metal impurities adhered to the substrate surface shift over to the washing solution. Since the washing solution is an acidic solution having pH of 2 to 4 and containing 0.0001 to 0.1 % by weight of an organic acid, the surfaces of the fine particles are charged to minus which is the same as that of the surface of the substrate. As the results, both of the surface potentials of the fine particles and the metal impurities become minus which is the same as that of the substrate whereby adhesion or re-adhesion to the substrate can be prevented. In case where no light is irradiated to the surface of the substrate, metal impurities near to the surface of the substrate cannot be removed any more when the reaction in the washing solution reaches to an equilibrium condition. However, when light is irradiated to the substrate surface as in the present invention, this photoirradiation brings minority carrier into existence near to the substrate surface, which reduces and dissociates an organic acid in the washing solution to make metal impurities into metal complex salts whereby an effect of removing metal impurities near to the substrate surface is enhanced.

An invention according to Claim 6 relates to a method of washing a semiconductor substrate which comprises washing a semiconductor substrate with a washing solution containing 0.0001 to 0.1 % by weight of an organic acid and 0.005 to 0.25 % by weight of hydrofluoric acid and having pH of 2 to 4 while irradiating light with a wavelength of at least 500 nm.

As shown in Figs. 3(a) and 3(b), a contaminated semiconductor substrate 11 is immersed in a washing solution 15 and light 20 with a wavelength of at least 500 nm is irradiated to the surface of the substrate 11. By further containing hydrofluoric acid (HF) in the washing solution defined in Claim 5, hydrofluoric acid removes a naturally oxidized film 12 formed on the surface of the semiconductor substrate 11, and fine particles 13 and metal impurities 14 on the naturally oxidized film 12 as well as metal impurities 14 contained in the naturally oxidized film are shifted over to the washing solution 15. Since the washing solution 15 is an acidic solution having pH of 2 to 4 and containing 0.005 to 0.25 % by weight of hydrofluoric acid and 0.0001 to 0.1 % by weight of an organic acid, the surfaces of the fine particles 13 are charged to minus which is the same as that of the substrate surface 11. Also, the metal impurities 14 liberated into the solution form a complex with organic acid molecules 16 to yield metal complex salts 17. This complex ion of the metal complex salt 17 is a minus ion. As a result, both of the surface potentials of the fine particles 13 and the metal impurities 14 become minus which is the same as that of the substrate 11 whereby adhesion or re-adhesion to the substrate can be prevented (Fig. 3(c)). In case where no light is irradiated to the surface of the substrate, metal impurities near to the surface of the substrate cannot be removed any more when the reaction in the washing solution reaches to an equilibrium condition. However, when light 20 is irradiated to the substrate surface as in the present invention, this photoirradiation brings minority carrier into existence near to the substrate surface, which reduces and dissociates an organic acid in the washing solution to make metal impurities into metal complex salts whereby an effect of removing metal impurities near to the substrate surface is enhanced. When the semiconductor substrate 11 is pulled up from the washing solution 15, the substrate 11 the surface of which is cleaned can be obtained (Fig. 3(d)).

An invention relating to Claim 7 is an invention according to Claim 5 or 6 and relates to a washing method wherein the organic acid is one or more organic acid selected from the group consisting of citric acid, succinic acid, EDTA, tartaric acid, salicylic acid, oxalic acid, acetic acid and formic acid.

The above-mentioned organic acids enumerated has a complexing effect of impurity metal ions which contaminate a substrate.

A method of Claim 8 relates to a washing method of a semiconductor substrate which contains a first washing step of washing a semiconductor substrate with a mixed solution of an organic acid and hydrofluoric acid with pH of 2 to 4, and a second washing step of washing said semiconductor substrate with an oxidizing solution.

In the first washing step, as in the invention relating to Claim 3 shown in Figs. 1(a) to 1(c), when a naturally oxidized film 12 is removed from a contaminated semiconductor substrate 11, fine particles 13 and metal impurities 14 on the naturally oxidized film 12 as well as metal impurities 14 contained in the naturally oxidized film are shifted over to the washing solution 15. As this time, each of the surface potentials of the fine particles 13 and the metal impurities 14 becomes minus which is the same as that of the substrate 11 whereby adhesion or re-adhesion to the substrate can be prevented. When the semiconductor substrate 11 is pulled up from the washing solution 15, a substrate 11 the surface of which is cleaned can be obtained.

In the second washing step, when the substrate washed in the first washing step is immersed in an oxidizing solution, a hydrophilic oxidized film is formed on the surface of the substrate by the oxidizing solution, and organic acids or organic substances adhered to the surface of the substrate are decomposed and removed without complexing metal impurities. By the formation of the oxidized film, attachment of fine particles in air to the surface of the substrate pulled up from the oxidizing solution can be prevented.

An invention relating to Claim 9 is an invention according to Claim 8, and is a method of washing a semiconductor substrate wherein the first washing step and the second washing step are each carried out at least twice.

By repeating the first washing step and the second washing step, the surface of the substrate can be more cleaned.

An invention according to Claim 10 is an invention relating to Claim 8 or 9, and is a method of washing a semicon-

ductor substrate wherein the mixed solution of the first washing step contains 0.0001 to 0.1 % by weight of an organic acid and 0.005 to 0.25 % by weight of hydrofluoric acid.

In order to sufficiently complex metal ions which are impurities of organic acids and to prevent fine particles from adhering to the substrate again, an organic acid and hydrofluoric acid in the above-mentioned concentration ranges are preferred.

An invention according to Claim 11 is an invention relating to Claim 8 or 10, and is a method of washing a semiconductor substrate wherein the organic acid is one or more organic acid selected from the group consisting of citric acid, succinic acid, EDTA, tartaric acid, salicylic acid, oxalic acid, acetic acid and formic acid.

The above-mentioned organic acids enumerated have a complexing action of metal ions which are impurities contaminating the substrate.

An invention according to Claim 12 is an invention relating to Claim 8 or 9, and is a method of washing a semiconductor substrate wherein the semiconductor substrate is subjected to ultrasonic washing with the mixed solution of the first washing step.

By carrying out ultrasonic washing, fine particles can be more firmly removed from the surface of the substrate.

An invention according to Claim 13 is an invention relating to Claim 8 or 9, and is a method of washing a semiconductor substrate wherein the oxidizing solution of the second washing step is a dissolved ozone aqueous solution, hydrogen peroxide solution or nitric acid.

The enumerated oxidizing solutions as mentioned above have actions of forming an oxidizing film at the surface of the substrate and of decomposing and removing organic acids or organic substances adhered to the surface of the substrate.

In the washing solution of the present invention, a kind of an organic acid and a concentration thereof are determined depending on the kind of metal impurities to be removed. pH of the washing solution is 2 to 4. A concentration of the organic acid in the washing solution is 0.0001 to 0.1 % by weight, preferably 0.003 to 0.006 % by weight. If it is less than 0.0001 % by weight, a complexing action of metal impurity ions liberated from the surface of the substrate is not sufficient, while if it exceeds 0.1 % by weight, there is a disadvantage that an amount of fine particles adhered again will increase.

As the organic acid of the present invention, in addition to citric acid, succinic acid, EDTA, suitable for the present invention are tartaric acid, salicylic acid, oxalic acid, acetic acid, formic acid and the like. One or more kinds of acids are optionally selected from the above-mentioned organic acids depending on the metal elements constituting the metal impurities.

Also, when hydrofluoric acid is contained in the washing solution, a concentration of the hydrofluoric acid is 0.005 to 0.25 % by weight. Particularly in the range of 0.005 to 0.10 % by weight is preferred and 0.05 to 0.1 % by weight is more preferred. If it is less than 0.005 % by weight, peeling effect of a naturally oxidized film on the surface of the semiconductor substrate is poor, while if it exceeds 0.25 % by weight, the washing solution becomes a strong acid with pH of less than 2, whereby dissociation of the organic acid in the washing solution is prevented so that its complexing action is lowered, and also, the surface potentials of the fine particles becomes plus so that fine particles adhere again to the surface of the substrate.

When light is irradiated at the washing, a wavelength of light to be irradiated to the semiconductor substrate is at least 500 nm, preferably 400 to 900 nm, more preferably 600 to 700 nm. If it is less than 500 nm, a photocatalytic effect near to the surface of the semiconductor substrate is weak and the organic acid is not to be reduced and dissociated. Further, the higher the intensity of illumination of light is, the larger the irradiated dose is, so that the amount of bringing carriers into existence becomes large and reduction and dissociation of the organic acid are promoted. According to the above, it can be considered that a complex ion-forming ability is improved and an effect of removing metal impurities near to the surface of the substrate is heightened.

In the invention according to Claim 8, the mixed solution of the first washing step is preferably a washing solution relating to Claim 1. As the oxidizing solution of the second washing step, there may be mentioned a dissolved ozone aqueous solution, hydrogen peroxide solution or nitric acid. Among them, the dissolved ozone aqueous solution is preferred since it is high purity, high oxidizing power with a low concentration and easily available. An ozone concentration of the dissolved ozone aqueous solution is preferably 0.5 ppm or more. If it is less than 0.5 ppm, it is difficult to form a hydrophilic oxidized film on the surface of the substrate, and decomposition and removal effects of organic acids or organic substances adhered to the surface of the substrate are lowered. Since a dissolution limit of ozone to pure water is about 25 ppm, the ozone concentration of the dissolved ozone aqueous solution is more preferably 5 to 25 ppm.

Next, a phenomenon in which metal impurities adheres to a semiconductor substrate represented by a silicon wafer and deposited thereon when the substrate is washed with hydrofluoric acid, and a phenomenon in which metal impurities adheres to the substrate and deposited thereon when the substrate is washed with hydrofluoric acid and an organic acid are explained.

(a) A phenomenon in which metal impurities adheres to a substrate and deposited thereon when the substrate is washed with hydrofluoric acid

When a metal ion is contained in a solution which does not etch the surface of a wafer and metal impurities in the solution adheres to the surface of a wafer, the metals adhering to the surface can be classified into two kinds one of which is an element which easily forms a silicide and the other is an element which easily forms a silicate. As the element easily forming a silicide, there may be mentioned Cu, Ni and the like which easily bind to silicon and as the element easily forming a silicate, there may be mentioned Fe, Al, Zn and the like which easily bind to a silicon oxide. For example, when a silicon wafer is washed with a high concentration hydrofluoric acid, a naturally oxidized film on the surface of the wafer is removed and about 90 % of the surface of the wafer is terminated by hydrogen atom. According to the above, a surface potential of the wafer is lowered and Cu, Ni, etc. which easily form a silicide accept an electron from the surface of the wafer to adhere to the surface of the wafer. Easiness of transfer the electron to an ion species such as a Cu ion, etc. from the surface of the wafer depends on an interfacial level in the solution. In the above-mentioned state, it can be considered that the interfacial level thereof is in the state near to that of the silicon wafer and electrons transfer through an electron transitional step so that this kind of a metal ion transfers to the surface of the wafer.

To the contrary, when a silicon wafer is washed with a low concentration hydrofluoric acid, an etching ability of the naturally oxidized film is lowered and a ratio of the naturally oxidized film remained at the surface of the wafer becomes large so that Fe, Al, Zn, etc. which easily form a silicate adhere to the surface of the wafer. In this state, interfacial levels are markedly apart from each other between the metal species to be adhered and the surface of the wafer whereby no transitional step of electrons as mentioned above does occur easily. In Fe ion, etc., an energy gap to go over in case where an oxide is formed by binding with oxygen is lower than that of directly binding with silicon. Thus, it can be considered that Fe ion, etc. would belong to chemical reaction system depending on both of contact frequencies of the Fe ion and a silicon oxide compound.

(b) A phenomenon in which metal impurities adheres to a substrate and deposited thereon when the substrate is washed with hydrofluoric acid and an organic acid

When a mixed solution of hydrofluoric acid and an organic acid is made a washing solution, adhesion and deposition phenomenon of the metal can be considered to be a complex system of the above-mentioned (a) as a base. That is, depending on how much amounts of hydrofluoric acid and an organic acid is present in the washing solution, the above-mentioned adhesion and deposition phenomenon will change. As a factor to determine the adhesion phenomenon, there are dissociation constant or ionization constant of the acid. When the constant is large, much amounts of protons are released and ion species of the acid increase. In the mixed system of hydrofluoric acid and an organic acid, it can be considered that an acid having a larger dissociation constant will be more predominantly dissociated.

When the respective first dissociation constants of hydrofluoric acid and various kinds of organic acids are arranged in order of size, the results are the following formula (1).



In the washing solution in which hydrofluoric acid and an organic acid are mixed of the present invention, whereas it has not yet been clarified sufficiently that how the adhesion and deposition phenomenon of metals changes by changing a kind of the organic acid or the concentration of hydrofluoric acid from the above-mentioned formula (1), it can be estimated as mentioned below.

(i) In case of a washing solution containing oxalic acid, EDTA or tartaric acid and hydrofluoric acid

When a silicon wafer contaminated by metal impurities is washed with an organic acid having a larger acid dissociation constant than that of hydrofluoric acid and hydrofluoric acid, dissociation of the organic acid predominantly occur and hydrofluoric acid does not dissociate than the case where it exists alone whereby it easily remaining the washing solution as an HF molecule. Thus, silicon oxide is decomposed by a chemical reaction with the HF molecule so that the surface of the wafer is terminated by hydrogen atoms. When an amount of the HF molecules is large, in other words, when the concentration of hydrofluoric acid is high, the naturally oxidized film can be removed and a metal which easily forms a silicide such as Cu will be easily adhered and deposited. However, decrease in an adsorbed amount accompanied by increase in an amount of the organic acid is based on a coordination effect of an organic acid ion. On the other hand, a metal which easily forms a silicate such as Fe becomes difficultly adhered and deposited. The metal such as Fe becomes easily formable of a complex ion due to increase in the concentration of the organic acid and an amount of deposit is lowered.

(ii) In case of a washing solution containing succinic acid or acetic acid and hydrofluoric acid

When a silicon wafer contaminated by metal impurities is washed with an organic acid having a smaller acid dissociation constant than that of hydrofluoric acid and hydrofluoric acid, dissociation of hydrofluoric acid is strong so that it can hardly be remained as a HF molecule and an etching ability of the naturally oxidized film is lowered. Thus, the naturally oxidized film is remained and when the concentration of hydrofluoric acid becomes high, a metal which easily forms a silicide such as Cu becomes to be difficultly adhered and deposited. On the other hand, a metal which easily forms a silicate such as Fe becomes to be easily adhered and deposited. However, a metal such as Fe easily forms a complex ion due to increase in the concentration of the organic acid so that an adhered amount to the surface of a wafer is lowered.

(iii) In case of a washing solution containing citric acid and hydrofluoric acid

Since there is substantially no difference in dissociation ability between citric acid and hydrofluoric acid, an acid with a higher concentration among the citric acid and the hydrofluoric acid dominates the system. That is, when the concentration of hydrofluoric acid is lower than that of the citric acid, citric acid becomes dominant so that hydrofluoric acid becomes to be difficultly dissociated and easily remained as an HF molecule. Thereby the naturally oxidized film is removed and a metal which easily forms a silicide such as Cu becomes to be easily adhered and deposited. To the contrary, when the concentration of hydrofluoric acid becomes higher than that of the hydrofluoric acid, dissociation of hydrofluoric acid dominates the system. However, an amount of HF molecules which are not dissociated is also increased so that the naturally oxidized film is removed and a metal which easily forms a silicide such as Cu becomes to be easily adhered and deposited. On the other hand, a metal which easily forms a silicate such as Fe also becomes to be easily adhered and deposited. However, the metal such as Fe becomes to be easily formed due to increase in the concentration of the organic acid and an adhered amount to the surface of the wafer is lowered.

(EXAMPLES)

Next, the present invention is explained in detail by referring to Examples and Comparative examples which do not limit the scope of the present invention.

(Examples 1 to 9)

As shown in Table 1, as an organic acid, 0.0006 % by weight, 0.006 % by weight and 0.06 % by weight of citric acids were mixed with pure water, respectively. To a citric acid aqueous solution containing 0.0006 % by weight of the acid were added 0.005 % by weight, 0.05 % by weight and 0.25 % by weight of hydrofluoric acid, respectively, to prepare washing solutions. Also, to a citric acid aqueous solution containing 0.006 % by weight of the acid were added 0.005 % by weight, 0.05 % by weight and 0.25 % by weight of hydrofluoric acid, respectively, to prepare washing solutions. Further, to a citric acid aqueous solution containing 0.06 % by weight of the acid were added 0.005 % by weight, 0.05 % by weight and 0.25 % by weight of hydrofluoric acid, respectively, to prepare washing solutions. pH of the respective washing solutions are shown in Table 4.

(Examples 10 to 15)

As shown in Table 1, as an organic acid, 0.00003 % by weight and 0.003 % by weight of succinic acids were mixed with pure water, respectively. To a succinic acid aqueous solution containing 0.00003 % by weight of the acid were added 0.005 % by weight, 0.05 % by weight and 0.25 % by weight of hydrofluoric acid, respectively, to prepare washing solutions. Also, to a succinic acid aqueous solution containing 0.003 % by weight of the acid were added 0.005 % by weight, 0.05 % by weight and 0.25 % by weight of hydrofluoric acid, respectively, to prepare washing solutions. pH of the respective washing solutions are shown in Table 4.

(Examples 16 to 21)

As shown in Table 2, as an organic acid, 0.00008 % by weight and 0.0008 % by weight of ethylenediaminetetraacetic acids (EDTA) were mixed with pure water, respectively. To an EDTA aqueous solution containing 0.00008 % by weight of the acid were added 0.005 % by weight, 0.05 % by weight and 0.25 % by weight of hydrofluoric acid, respectively, to prepare washing solutions. Also, to an EDTA aqueous solution containing 0.0008 % by weight of the acid were added 0.005 % by weight, 0.05 % by weight and 0.25 % by weight of hydrofluoric acid, respectively, to prepare washing solutions. pH of the respective washing solutions are shown in Table 4.

(Examples 22 to 27)

As shown in Table 2, as an organic acid, 0.0003 % by weight and 0.003 % by weight of tartaric acids were mixed with pure water, respectively. To a tartaric acid aqueous solution containing 0.0003 % by weight of the acid were added 0.005 % by weight, 0.05 % by weight and 0.25 % by weight of hydrofluoric acid, respectively, to prepare washing solutions. Also, to a tartaric acid aqueous solution containing 0.003 % by weight of the acid were added 0.005 % by weight, 0.05 % by weight and 0.25 % by weight of hydrofluoric acid, respectively, to prepare washing solutions. pH of the respective washing solutions are shown in Table 4.

(Examples 28 to 36)

As shown in Table 3, as an organic acid, 0.00027 % by weight, 0.0027 % by weight and 0.027 % by weight of oxalic acids were mixed with pure water, respectively. To an oxalic acid aqueous solution containing 0.00027 % by weight of the acid were added 0.005 % by weight, 0.05 % by weight and 0.25 % by weight of hydrofluoric acid, respectively, to prepare washing solutions. Also, to an oxalic acid aqueous solution containing 0.0027 % by weight of the acid were added 0.005 % by weight, 0.05 % by weight and 0.25 % by weight of hydrofluoric acid, respectively, to prepare washing solutions. Further, to an oxalic acid aqueous solution containing 0.027 % by weight of the acid were added 0.005 % by weight, 0.05 % by weight and 0.25 % by weight of hydrofluoric acid, respectively, to prepare washing solutions. pH of the respective washing solutions are shown in Table 5.

(Examples 37 to 42)

As shown in Table 3, as an organic acid, 0.00018 % by weight and 0.018 % by weight of acetic acids were mixed with pure water, respectively. To an acetic acid aqueous solution containing 0.00018 % by weight of the acid were added 0.005 % by weight, 0.05 % by weight and 0.25 % by weight of hydrofluoric acid, respectively, to prepare washing solutions. Also, to an acetic acid aqueous solution containing 0.018 % by weight of the acid were added 0.005 % by weight, 0.05 % by weight and 0.25 % by weight of hydrofluoric acid, respectively, to prepare washing solutions. pH of the respective washing solutions are shown in Table 5.

To these washing solution at room temperature were compulsory added five metal ions of Fe, Ni, Cu, Zn and Al in amounts of each 100 ppb and polystyrene latex particles with a particle size of 0.294 μm in an amount of 8000 particles/0.1 ml. The above-mentioned metal concentrations are about 1000-folds or more as compared with the metal concentrations contained in a usual solution. On the other hand, a silicon wafer cleaned with an SC1 solution (a mixed solution of $\text{H}_2\text{O}:\text{H}_2\text{O}_2(30\%):\text{NH}_4\text{OH}(29\%)=5:1:0.25$) was prepared and the silicon wafer was immersed in the above-mentioned washing solutions for 10 minutes. Subsequently, the wafer was rinsed by ultrapure water for 10 minutes and water drops on the surface of the wafer were removed by centrifugal force to dry the wafer.

According to the above procedure, peeling off of a naturally oxidized film on the surface of the wafer, complexing ions of metal impurities and control of each surface potential of the wafer, fine particles and metal impurities were carried out as mentioned above to clean the silicon wafer.

(Comparative example 1)

The conventional RCA washing method is made Comparative example 1. That is, in an SC1 solution (a mixed solution of $\text{H}_2\text{O}:\text{H}_2\text{O}_2(30\%):\text{NH}_4\text{OH}(29\%)=5:1:1$) to which the same metal ions and fine particles used in Examples were added with the same amounts, a silicon wafer cleaned by another SC1 solution was immersed, heated to 75 to 80 °C and maintained at 80 °C for 10 minutes. After this silicon wafer was rinsed by ultrapure water, the wafer was immersed in a mixed solution of $\text{H}_2\text{O}:\text{HF}(49\%)=50:1$ for 15 seconds and further rinsed by ultrapure water. Subsequently, the rinsed silicon wafer was immersed in an SC2 solution (a mixed solution of $\text{H}_2\text{O}:\text{H}_2\text{O}_2(30\%):\text{HCl}(37\%)=6:1:1$), heated to 75 to 80 °C and maintained at 80 °C for 10 minutes. Thereafter, the silicon wafer was rinsed by ultrapure water in the same manner as in above-mentioned Examples and dried.

(Comparative example 2)

A washing solution was prepared by adding 1 % by weight of hydrofluoric acid to a solution prepared by mixing 0.005 % by weight of ethylenediaminetetraacetic acid as an organic acid with pure water and pH of the solution was adjusted to 1. To the washing solution were added metal ions and fine particles which are similar to those used in Examples with the same amounts, and then a silicon wafer was immersed in the washing solution for 10 minutes. Thereafter, the silicon wafer was rinsed by ultrapure water in the same manner as in the above-mentioned Examples and dried.

(Comparative example 3)

5 A washing solution was prepared by adding 0.05 % by weight of hydrofluoric acid to pure water. To the washing solution were added metal ions and fine particles which are similar to those used in Examples with the same amounts, and then a silicon wafer was immersed in the washing solution for 10 minutes. Thereafter, the silicon wafer was rinsed by ultrapure water in the same manner as in the above-mentioned Examples and dried.

(Comparative example 4)

10 A washing solution was prepared by adding 0.25 % by weight of hydrofluoric acid to pure water. To the washing solution were added metal ions and fine particles which are similar to those used in Examples with the same amounts, and then a silicon wafer was immersed in the washing solution for 10 minutes. Thereafter, the silicon wafer was rinsed by ultrapure water in the same manner as in the above-mentioned Examples and dried.

15 (Comparative test and evaluation)

(a) Metal impurities concentrations

20 Metal impurities concentrations were measured on the surface of the silicon wafers after washing them with washing solutions prepared in Examples 1 to 4, 7 to 11, 14, 15, 17, 18, 21 to 23, 26 to 29, 31, 34, 35, 37 to 42 and Comparative example 1. These metal impurities concentrations were measured by dropping a mixed acid of hydrofluoric acid and nitric acid to the center portion of the silicon wafer after washing, and after developing liquid drops to cover the whole surface of the silicon wafer, and recovering the liquid drops to analyze them by atomic-absorption spectroscopy. The results are shown in Table 1 to Table 3.

25 From Table 1 to Table 3, adhesion and deposition phenomenon of metals of the above-mentioned (i) to (iii) were confirmed.

(b) Relatively increased amount of particles

30 The number of remained particles on the surface of the respective wafers after washing them with each of washing solutions prepared in Examples 1, 4, 7, 12, 15, 18, 20, 22, 24, 26, 31 and Comparative examples 1 to 4 was measured. The number of remained particles was measured by counting particles with a particle size of 0.2 μm or more remained on the surface of the silicon wafer after washing with a particle counter. The results are shown in Table 4 and Table 5.

35 As clearly seen from Table 4 and Table 5, in each washing solution of the above-mentioned Examples and Comparative example 1, 8 to 78 particles are remained. To the contrary, in washing solutions of Comparative examples 2 to 4, 218 to 2123 particles are remained. From the above results, it can be understood that the washing solutions of Examples well wash out the particles as compared with those of Comparative examples 2 to 4.

Table 1

		Hydrofluoric acid concentration (wt%)	Name of Organic acid	Organic acid concentration (wt%)	Metal impurity concentration				
					Fe	Ni	Zn	Cu	Al
Example	1	0.005	Citric acid	0.0006	4.5×10^{11}	$<1 \times 10^{10}$	$<1 \times 10^{10}$	4.3×10^{14}	$<1 \times 10^{10}$
	2			0.006	2.6×10^{11}	$<1 \times 10^{10}$	$<1 \times 10^{10}$	2.6×10^{14}	$<1 \times 10^{10}$
	3			0.06	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	6.2×10^{12}	$<1 \times 10^{10}$
	4	0.05		0.0006	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$
	5			0.006	-	-	-	-	-
	6			0.06	-	-	-	-	-
	7	0.25		0.0006	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	2.7×10^{12}	$<1 \times 10^{10}$
	8			0.006	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	3.0×10^{12}	$<1 \times 10^{10}$
	9			0.06	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	2.9×10^{12}	$<1 \times 10^{10}$
	10	0.005	Succinic acid	0.00003	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	7.3×10^{11}	$<1 \times 10^{10}$
	11			0.003	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	1×10^{12}	$<1 \times 10^{10}$
	12	0.05		0.00003	-	-	-	-	-
	13			0.003	-	-	-	-	-
	14	0.25		0.00003	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	1.5×10^{11}	-
	15			0.003	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	1×10^{11}	-

Table 2

		Hydrofluoric acid concentration (wt%)	Name of Organic acid	Organic acid concentration (wt%)	Metal impurity concentration				
					Fe	Ni	Zn	Cu	Al
Example	16	0.005	EDTA	0.00008	-	-	-	-	-
	17			0.0008	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$
	18	0.05		0.00008	-	-	-	-	-
	19			0.0008	2×10^{10}	$<1 \times 10^{10}$	$<1 \times 10^{10}$	2×10^{10}	$<1 \times 10^{10}$
	20	0.25		0.00008	-	-	-	-	-
	21			0.0008	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	4×10^{11}	$<1 \times 10^{10}$
	22	0.005	Tartaric acid	0.0003	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	1.1×10^{13}	$<1 \times 10^{10}$
	23			0.003	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	7.7×10^{12}	$<1 \times 10^{10}$
	24	0.05		0.0003	-	-	-	-	-
	25			0.003	-	-	-	-	-
	26	0.25		0.0003	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	1.8×10^{12}	$<1 \times 10^{10}$
	27			0.003	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	4.3×10^{11}	$<1 \times 10^{10}$

Table 3

		Hydrofluoric acid concentration (wt%)	Name of Organic acid	Organic acid concentration (wt%)	Metal impurity concentration				
					Fe	Ni	Zn	Cu	Al
Example	28	0.005	Oxalic acid	0.00027	-	-	-	4.5×10^{11}	$<1 \times 10^{10}$
	29			0.0027	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$
	30			0.027	-	-	-	-	-
	31	0.05		0.00027	-	-	-	1.6×10^{13}	1.2×10^{10}
	32			0.0027	-	-	-	-	-
	33			0.027	-	-	-	-	-
	34	0.25		0.00027	2.6×10^{10}	$<1 \times 10^{10}$	$<1 \times 10^{10}$	4.8×10^{13}	$<1 \times 10^{10}$
	35			0.0027	-	$<1 \times 10^{10}$	$<1 \times 10^{10}$	4.3×10^{12}	$<1 \times 10^{10}$
	36			0.027	-	-	-	-	-
	37	0.005	Acetic acid	0.00018	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	9×10^{12}	4.9×10^{10}
	38			0.018	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	1.5×10^{12}	$<1 \times 10^{10}$
	39	0.05		0.00018	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	5.2×10^{11}	1.3×10^{10}
	40			0.018	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	4.7×10^{11}	1×10^{10}
	41	0.25		0.00018	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	1.1×10^{12}	$<1 \times 10^{10}$
	42			0.018	$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	5.4×10^{11}	$<1 \times 10^{10}$
Comparative example	1	(RCR Washing)			$<1 \times 10^{10}$	$<1 \times 10^{10}$	$<1 \times 10^{10}$	1.5×10^{11}	4.0×10^{10}

Table 4

		Hydrofluoric acid concentration (wt%)	Name of organic acid	Organic acid concentration (wt%)	pH	Adhered number of particles having 0.2 μm or more
Example	1	0.005	Citric acid	0.0006	3.0	12
	2			0.006	2.9	—
	3			0.06	2.3	—
	4	0.05		0.0006	2.8	15
	5			0.006	2.4	—
	6			0.06	2.2	—
	7	0.25		0.0006	2.0	64
	8			0.006	2.0	—
	9			0.06	2.0	—
	10	0.005	Succinic acid	0.00003	3.2	—
	11			0.003	3.2	—
	12	0.05		0.00003	2.7	51
	13			0.003	3.4	—
	14	0.25		0.00003	2.0	—
	15			0.003	2.0	72
	16	0.005	EDTA	0.00008	3.1	—
	17			0.0008	3.0	—
	18	0.05		0.00008	2.4	8
	19			0.0008	2.3	—
	20	0.25		0.00008	2.0	16
	21			0.0008	2.0	—
	22	0.005	Tartaric acid	0.0003	3.1	49
	23			0.003	2.4	—
	24	0.05		0.0003	2.8	41
	25			0.003	2.1	—
	26	0.25		0.0003	2.0	78
	27			0.003	2.0	—

Table 5

		Hydrofluoric acid concentration (wt%)	Name of organic acid	Organic acid concentration (wt%)	pH	Adhered number of particles having 0.2 μm or more	
Example	28	0.005	Oxalic acid	0.00027	3.0	—	
	29			0.0027	2.6	—	
	30			0.027	2.0	—	
	31	0.05		0.00027	2.9	43	
	32			0.0027	2.7	—	
	33			0.027	2.4	—	
	34	0.25		0.00027	2.0	—	
	35			0.0027	2.0	—	
	36			0.027	2.0	—	
	37	0.005		Succinic acid	0.00018	3.1	—
	38				0.0018	2.9	—
	39	0.05			0.00018	2.9	—
	40		0.0018		2.8	—	
	41	0.25	0.00018		2.0	—	
	42		0.0018		2.0	—	
Comparative example	1	(RCA washing)			—	10	
	2	1.00	EDTA	0.005	1.0	2123	
	3	0.05	None	—	—	218	
	4	0.25		—	—	1542	

Example 43)

First, Fe ion is added to an SC1 solution (a mixed solution of $\text{H}_2\text{O}:\text{H}_2\text{O}_2(30\%):\text{NH}_4\text{OH}(29\%)=5:1:0.25$) in an amount of 100 ppb, and the mixture was raised to 80 °C. Then, a silicon wafer was immersed in the solution of 80 °C for 10 minutes, rinsed for 10 minutes and water drops on the surface of the wafer were removed and dried.

On the other hand, a washing solution in which 0.006 % by weight of citric acid was added to pure water as an organic acid, having pH of 4.0 was prepared. The above-mentioned metal-contaminated silicon wafer was immersed in the washing solution at room temperature for 10 minutes, and irradiated light having an intensity of illumination of 100,000 lux and a wavelength of 500 nm to the surface of the silicon wafer. Thereafter, this silicon wafer was rinsed with ultrapure water for 10 minutes. According to the above procedure, peeling off of a naturally oxidized film on the surface of the wafer, complexing ions of metal impurities and control of each surface potential of the wafer, fine particles and metal impurities were carried out as mentioned above to clean the silicon wafer.

Example 44)

In the same manner as in Example 43 except for changing the wavelength of the light to be irradiated to 550 nm, a silicon wafer was washed.

Example 45)

In the same manner as in Example 43 except for changing the wavelength of the light to be irradiated to 600 nm, a silicon wafer was washed.

(Example 46)

In the same manner as in Example 43 except for changing the wavelength of the light to be irradiated to 650 nm, a silicon wafer was washed.

(Comparative example 5)

In the same manner as in Example 43 except for no light is irradiated, a silicon wafer was washed.

(Comparative example 6)

In the same manner as in Example 43 except for changing the wavelength of the light to be irradiated to 450 nm, a silicon wafer was washed.

Fe concentrations on the surfaces of the silicon wafers of Examples 43 to 46 and Comparative examples 5 and 6 after washing were examined. These metal impurities concentrations were measured by dropping a mixed acid of hydrofluoric acid and nitric acid to the center portion of the silicon wafer after washing, and after developing liquid drops to cover the whole surface of the silicon wafer, and recovering the liquid drops to analyze them by atomic-absorption spectroscopy. The results are shown in Fig. 4.

As can be clearly seen from Fig. 4, when a wavelength of irradiated light is made 500 nm or more as in Examples 43 to 46, it can be understood that Fe concentrations became about one order smaller than those of Comparative examples 5 and 6.

(Example 47)

A silicon wafer to the surface of which is adhered five metal of Al, Fe, Cu, Ni and Zn previously was prepared by the following method. First, to a SC1 solution (a mixed solution of $\text{H}_2\text{O}:\text{H}_2\text{O}_2(30\%):\text{NH}_4\text{OH}(29\%)=5:1:0.25$) was compulsorily added five metal ions of Al, Fe, Cu, Ni and Zn in amounts of each 100 ppb. This solution was raised to 80 °C, and after immersing the silicon wafer in the solution at 80 °C for 10 minutes, the wafer was rinsed for 10 minutes, then it was rinsed and water drops on the surface of the wafer were removed by centrifugal force and dried.

As the first washing step, a mixed solution was prepared by adding 0.05 % by weight of hydrofluoric acid to a solution in which 0.006 % by weight of citric acid was added to pure water as an organic acid, and adjusted to pH 3.0 was prepared. In the mixed solution at room temperature was immersed the silicon wafer contaminated by the above-mentioned metal impurities and then washed under ultrasonic wave for 10 minutes. Thereafter, this silicon wafer was rinsed with ultrapure water for 10 minutes.

Next, as the second washing step, this washed silicon wafer was immersed in a dissolved ozone aqueous solution with an ozone concentration of 8 ppm for 10 minutes. Thereafter, this silicon wafer was rinsed with ultrapure water for 10 minutes.

Subsequently, after the silicon wafer was washed again with the above-mentioned first washing step, and then washed again with the above-mentioned second washing step. That is, the first washing step and the second washing step were each carried out twice, respectively.

(Comparative example 7)

The conventional RCA washing method is made Comparative example 7. That is, in the same manner as in Example 47, a silicon wafer contaminated with metal impurities was immersed in an SC1 solution (a mixed solution of $\text{H}_2\text{O}:\text{H}_2\text{O}_2(30\%):\text{NH}_4\text{OH}(29\%)=5:1:1$), heated to 75 to 80 °C and maintained at 80 °C for 10 minutes. After the silicon wafer was rinsed by ultrapure water, it was immersed in a mixed solution of $\text{H}_2\text{O}:\text{HF}(49\%)=50:1$ for 15 seconds, and further rinsed by ultrapure water. Subsequently, the silicon wafer rinsed was immersed in an SC2 solution (a mixed solution of $\text{H}_2\text{O}:\text{H}_2\text{O}_2(30\%):\text{HCl}(37\%)=6:1:1$), heated to 75 to 80 °C and maintained at 80 °C for 10 minutes. Thereafter, the silicon wafer was rinsed by ultrapure water in the same manner as in Example 47.

After this silicon wafer was washed again with the SC1 solution as mentioned above, it was further washed again with the SC2 solution as mentioned above. That is, washing with the SC1 solution and washing with the SC2 solution were carried out each twice.

(Comparative test and evaluation)

Metal impurities concentrations on each surface of the respective silicon wafers after washing of Example 47 and Comparative example 7 were measured. This metal impurities concentrations were measured by dropping a mixed acid

of hydrofluoric acid and nitric acid to the center portion of the silicon wafer after washing, and after developing liquid drops to cover the whole surface of the silicon wafer, and recovering the liquid drops to analyze them by atomic-absorption spectroscopy. The results are shown in Fig. 5. As clearly seen from Fig. 5, it can be found that, in the wafer of Example 47, except for Ni concentration which was the same level, there are good washing effects with regard to the other five kinds of metals with the order of one digit as compared with the wafer of Comparative example 7 according to the conventional RCA washing method. Particularly, four kinds of metals of Al, Fe, Ni and Zn were each 10×10^8 atoms/cm² or less. Incidentally, an arrow to downward of Fe and Ni means lower than detection limit.

As described above, according to the washing method of Claim 3, three actions of peeling a naturally oxidized film on the surface of the substrate, complex ionization of metal impurities, and control of each surface potential of the substrate, fine particles and metal impurities can be carried out with a single bath, and both of metal impurities and fine particles can be well removed from the semiconductor substrate. As the results, as compared with the conventional RCA washing method, washing steps can be simplified, chemical solutions for washing are only two kinds of hydrofluoric acid and an organic acid, washing can be carried out within a short period of time with a small-sized apparatus and a washing cost can be reduced.

Also, according to the washing method of the invention relating to Claim 5 or 6, the photoirradiation brings minority carrier into existence near to the substrate surface, which reduces and dissociates an organic acid in the washing solution to make metal impurities into metal complex salts whereby an effect of removing metal impurities near to the surface of the substrate can be heightened. Chemical solution for washing is only one kind of an organic acid alone, or two kinds of hydrofluoric acid and an organic acid.

Further, according to the washing method of the invention relating to Claim 8, three actions of peeling a naturally oxidized film on the surface of the substrate, complex ionization of metal impurities, and control of each surface potential of the substrate, fine particles and metal impurities can be carried out in the first washing step to remove both of metal impurities and fine particles well from the semiconductor substrate, and then, in the second step, an oxidized film is formed on the surface of the substrate and simultaneously an organic acid or an organic material adhered to the surface of the substrate is decomposed and removed. Thus, as compared with the conventional RCA washing method, both of metal impurities and fine particles can be well removed, and chemical solutions for washing may be only three kinds of hydrofluoric acid solution and an oxidizing solution.


Claims

1. A washing solution of a semiconductor substrate comprising 0.0001 to 0.1 % by weight of an organic acid and 0.005 to 0.25 % by weight of hydrofluoric acid and having pH of 2 to 4.
2. The washing solution of a semiconductor substrate according to Claim 1, wherein said organic acid is one or more organic acid selected from the group consisting of citric acid, succinic acid, ethylenediaminetetraacetic acid, tartaric acid, salicylic acid, oxalic acid, acetic acid and formic acid.
3. A method of washing a semiconductor substrate which comprises washing a semiconductor substrate with a washing solution containing 0.0001 to 0.1 % by weight of an organic acid and 0.005 to 0.25 % by weight of hydrofluoric acid and having pH of 2 to 4.
4. The method of washing a semiconductor substrate according to Claim 3, wherein the organic acid is one or more organic acid selected from the group consisting of citric acid, succinic acid, EDTA, tartaric acid, salicylic acid, oxalic acid, acetic acid and formic acid.
5. A method of washing a semiconductor substrate which comprises washing a semiconductor substrate with a washing solution containing 0.0001 to 0.1 % by weight of an organic acid and having pH of 2 to 4 while irradiating light with a wavelength of at least 500 nm.
6. A method of washing a semiconductor substrate which comprises washing a semiconductor substrate with a washing solution containing 0.0001 to 0.1 % by weight of an organic acid and 0.005 to 0.25 % by weight of hydrofluoric acid and having pH of 2 to 4 while irradiating light with a wavelength of at least 500 nm.
7. The method of washing a semiconductor substrate according to Claim 5 or 6, wherein the organic acid is one or more organic acid selected from the group consisting of citric acid, succinic acid, EDTA, tartaric acid, salicylic acid, oxalic acid, acetic acid and formic acid.
8. A method of washing a semiconductor substrate which comprises


a first washing step of washing a semiconductor substrate with a mixed solution of an organic acid and hydrofluoric acid with pH of 2 to 4, and
a second washing step of washing said semiconductor substrate with an oxidizing solution.

- 5 9. The method of washing a semiconductor substrate according to Claim 8, wherein the first washing step and the second washing step are each carried out at least twice.
- 10 10. A method of washing a semiconductor substrate according to Claim 8 or 9, wherein the mixed solution of the first washing step contains 0.0001 to 0.1 % by weight of an organic acid and 0.005 to 0.25 % by weight of hydrofluoric acid.
- 15 11. The method of washing a semiconductor substrate according to Claim 8 or 10, wherein the organic acid is one or more organic acid selected from the group consisting of citric acid, succinic acid, EDTA, tartaric acid, salicylic acid, oxalic acid, acetic acid and formic acid.
- 20 12. The method of washing a semiconductor substrate according to Claim 8 or 9, wherein the semiconductor substrate is subjected to ultrasonic washing with the mixed solution of the first washing step.
- 25 13. The method of washing a semiconductor substrate according to Claim 8 or 9, wherein the oxidizing solution of the second washing step is a dissolved ozone aqueous solution, hydrogen peroxide solution or nitric acid.
- 30
- 35
- 40
- 45
- 50
- 55


[Fig. 1]




【Fig. 2】




[Fig. 3]




【F i g. 4】



【Fig. 5】



[Fig. 6]



Prior Art

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 859 404 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
26.05.1999 Bulletin 1999/21

(51) Int. Cl.⁶: H01L 21/306, C11D 7/00

(43) Date of publication A2:
19.08.1998 Bulletin 1998/34

(21) Application number: 98100625.7

(22) Date of filing: 15.01.1998

(84) Designated Contracting States:
AT BE CH DE DK ES FI FR GB GR IE IT LI LU MC
NL PT SE

Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 16.01.1997 JP 5610/97
16.01.1997 JP 5611/97
16.01.1997 JP 5612/97

(71) Applicants:

- Mitsubishi Materials Silicon Corporation
Chiyoda-ku, Tokyo (JP)
- MITSUBISHI MATERIALS CORPORATION
Chiyoda-ku, Tokyo (JP)

(72) Inventors:

- Matsuo, Chizuko
5-1 Ohtemachi 1-chome, Chiyoda-ku, Tokyo (JP)
- Kishimoto, Mikio,
c/o Central Research Institute
Omiya-shi, Saitama-ken (JP)
- Takaishi, Kazushige
5-1 Ohtemachi 1-chome, Chiyoda-ku, Tokyo (JP)


(74) Representative:

Dost, Wolfgang, Dr.rer.nat., Dipl.-Chem. et al
Patent- und Rechtsanwälte
Bardehle . Pagenberg . Dost . Altenburg .
Geissler . Isenbruck
Galileiplatz 1
81679 München (DE)

(54) Washing solution of semiconductor substrate and washing method using the same

(57) Disclosed is a washing solution of a semiconductor substrate which comprises 0.0001 to 0.1 % by weight of an organic acid and 0.005 to 0.25 % by weight of hydrofluoric acid and has pH of 2 to 4. When a contaminated substrate is immersed in a washing solution, a naturally oxidized film on the surface of the substrate is removed by hydrofluoric acid, and fine particles on the film, metal impurities and metal impurities in the film transfer to the liquid. Since the washing solution is an acidic solution containing an organic acid and having pH of 2 to 4, fine particles are charged to minus as those of the fine particles, and the metal impurities ions in the liquid becomes minus complex ions due to complexing effect of the organic acid. As the results, surface potentials of the respective fine particles and metal impurities are each minus which is the same as that of surface potential of the substrate so that adhesion or re-adhesion to the substrate can be prevented.

[Fig. 1]





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 98 10 0625

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X	WO 94 27314 A (IMEC INTER UNI MICRO ELECTR ;VERHAVERBEKE STEVEN (BE); GEUSENS WAL) 24 November 1994 * page 3, line 22 - page 4, line 12 *	1-4	H01L21/306 C11D7/00
Y	* page 8, line 19 - page 9, line 18; claims 1-6; table 2 *	6-8,10, 11,13	
X	US 4 181 623 A (DILLARSTONE ALAN ET AL) 1 January 1980 * abstract * * column 1, line 29 - line 52; claim 1 *	1,2	
Y	EP 0 571 950 A (TEXAS INSTRUMENTS INC) 1 December 1993 * page 4, line 12 - line 25 * * page 7, line 53 - page 8, line 28; table A *	5-7	
Y	FR 2 722 511 A (ONTRAK SYSTEMS INC) 19 January 1996 * page 12, line 16 - page 17, line 35; figure 1C *	5,7	
Y	ANONYMOUS: "Silicon Surface Cleaning Process. October 1977." IBM TECHNICAL DISCLOSURE BULLETIN, vol. 20, no. 5, October 1977, pages 1746-1747, XP002095501 New York, US * the whole document *	8,10,11, 13	TECHNICAL FIELDS SEARCHED (Int.Cl.6) H01L
A	WO 96 26538 A (ADVANCED MICRO DEVICES INC) 29 August 1996 * page 3, line 25 - page 6, line 19 * * page 7, line 14 - page 9, line 7; tables 1-3 *	1-4	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 3 March 1999	Examiner Micke, K
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons</p> <p>& : member of the same patent family, corresponding document</p>			

EPO FORM 1503.03.82 (P04C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 98 10 0625

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A	PATENT ABSTRACTS OF JAPAN vol. 095, no. 001, 28 February 1995 & JP 06 291099 A (SUMITOMO SITIX CORP), 18 October 1994 * abstract *	5,7	
A	DE 195 15 024 A (WACKER SILTRONIC HALBLEITERMAT) 31 October 1996 * page 2, line 3 - line 68 *	5,7	
A	US 5 382 296 A (ANTTILA OLLI) 17 January 1995 * column 3, line 45 - line 60 *	5,7	
A	DE 195 21 389 A (MITSUBISHI ELECTRIC CORP) 13 June 1996 * column 7, line 52 - column 10, line 23 * * column 24, line 28 - line 40 *	12,13	
A	EP 0 674 343 A (SHINETSU HANDOTAI KK) 27 September 1995 * page 3, line 7 - page 4, line 11 * * page 6, line 16 - line 35 *	8-13	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
Place of search THE HAGUE		Date of completion of the search 3 March 1999	Examiner Micke, K.
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03/82 (P04C01)



European Patent
Office

Application Number
EP 98 10 0625

CLAIMS INCURRING FEES

The present European patent application comprised at the time of filing more than ten claims.

- ☐ Only part of the claims have been paid within the prescribed time limit. The present European search report has been drawn up for the first ten claims and for those claims for which claims fees have been paid, namely claim(s):
- ☐ No claims fees have been paid within the prescribed time limit. The present European search report has been drawn up for the first ten claims.

LACK OF UNITY OF INVENTION

The Search Division considers that the present European patent application does not comply with the requirements of unity of invention and relates to several inventions or groups of inventions, namely:

see sheet B

- ☒ All further search fees have been paid within the fixed time limit. The present European search report has been drawn up for all claims.
- ☐ Only part of the further search fees have been paid within the fixed time limit. The present European search report has been drawn up for those parts of the European patent application which relate to the inventions in respect of which search fees have been paid, namely claims:
- ☐ None of the further search fees have been paid within the fixed time limit. The present European search report has been drawn up for those parts of the European patent application which relate to the invention first mentioned in the claims, namely claims:



European Patent
Office

LACK OF UNITY OF INVENTION
SHEET B

Application Number
EP 98 10 0625

The Search Division considers that the present European patent application does not comply with the requirements of unity of invention and relates to several inventions or groups of inventions, namely:

1. Claims: 1-4,6,7

Method for washing a semiconductor substrate with a solution containing HF and an organic acid with specified concentrations and pH; and solution therefor.

2. Claims: 5,7

Method of washing a substrate using organic acid of specified concentration and pH with light irradiation.

3. Claims: 8-13

Two-step-process for washing substrate involving a mixture of organic acid and HF with unspecified concentrations.

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 98 10 0625

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

03-03-1999

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9427314 A	24-11-1994	NONE	
US 4181623 A	01-01-1980	GB 1571438 A	16-07-1980
		AU 521767 B	29-04-1982
		AU 3358978 A	30-08-1979
		BE 864914 A	03-07-1978
		CA 1092004 A	23-12-1980
		FR 2384018 A	13-10-1978
EP 0571950 A	01-12-1993	EP 0702400 A	20-03-1996
		JP 6061217 A	04-03-1994
		US 5695569 A	09-12-1997
FR 2722511 A	19-01-1996	DE 19525521 A	21-03-1996
		JP 8187475 A	23-07-1996
WO 9626538 A	29-08-1996	US 5662769 A	02-09-1997
		EP 0811244 A	10-12-1997
DE 19515024 A	31-10-1996	CN 1124763 A	19-06-1996
		EP 0698917 A	28-02-1996
		FI 953947 A	26-02-1996
		JP 2709452 B	04-02-1998
		JP 8100195 A	16-04-1996
		US 5695572 A	09-12-1997
US 5382296 A	17-01-1995	FI 910946 A	28-08-1992
		EP 0501492 A	02-09-1992
		JP 5090235 A	09-04-1993
DE 19521389 A	13-06-1996	JP 8162425 A	21-06-1996
		IT MI951994 A	06-06-1996
EP 0674343 A	27-09-1995	JP 2762230 B	04-06-1998
		JP 7263403 A	13-10-1995
		US 5484748 A	16-01-1996

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82